

# SARCOAT PW38 EXTRA

Last Updated: 09.01.2025  
Product Code: IP0916



SARCOAT PW38 EXTRA is a high quality, wax film long term rust preventative with a combination of dewatering additive technology together with film-forming corrosion prevention capabilities to provide extensive long-term protection.

Being solvent deposited this wax film corrosion preventive provides long term corrosion protection to all types of components stored outdoors including bar and box sections, aerospace applications such as high-flying aircraft.

## **APPLICATION**

Use as received, it is recommended that the product is stirred or shaken well before use. In low temperatures, product may gel, but will return to normal consistency under standard working conditions. Apply by spray or brush in a wellventilated area. Leaves a firm, waxy film on drying, which can be removed when required using hydrocarbon solvents, such as white spirit. If applied by brushing or swabbing extra care must be taken to ensure adequate coverage and that adventitious dirt particulates or brush fibres are not inadvertently introduced which may remain in the film as they can significantly detract from anti-corrosion performance. The ideal application temperature for this product is 15 – 25°C. As below 15°C it will be very viscous.

## **BENEFITS**

- Contains a highly-efficient dewatering agent to quickly and effectively remove moisture from treated metal surfaces, before leaving a firm, waxy deposit on drying.
- Offers exceptional long-term corrosion protection indoors, and outdoors undercover, for over 5 years, and up to 2 years for open outdoor component storage.
- Compatible with all types of ferrous and non-ferrous metals.
- Excellent penetration qualities to protect normally inaccessible areas.
- Ideal for long term protection of all metal stocks and agricultural machinery, as well as both car and commercial vehicle panels, underbodies etc. especially during storage and restoration.

## **PERFORMANCE PROFILE**

Indoor Protection	5 Years
Outdoor Protection Covered	3 Years
Outdoor Protection Uncovered	2 Years

## **TYPICAL PROPERTIES**

Appearance	Opaque fluid
Film thickness	40-50 microns
Solids Content %	34-36
Density @ 15.6°C	0.83
Indoor protection	5 years +
Outdoor protection	up to 2 years
Salt Spray ASTM B117	>1000 hours
Coverage	7m <sup>2</sup> per litre at 50 micron
Drying time	@ 20°C to 50 µ film thickness, 3 hours.

## **HEALTH & SAFETY**

Please refer to the Safety Data Sheet, freely available, for product handling and disposal advice. Please note that the SDS includes

# SARCOAT PW38 EXTRA

Last Updated: 09.01.2025  
Product Code: IP0916



handling, storage, health and disposal information which should be passed on to anyone else who comes in contact with our product. Additional advice can also be obtained from your local representative.

NOTE: Read and understand all precautions on container labels before using this product.